

MICRODENSE®

P1510.1403

WBM/OBM Drilling

Product Description

MICRODENSE is micronized ilmenite or FeTiO_3 . It can be used on its own, with barite, Micromax or other weight materials. It enables the production of low Rheology fluids for good ECD management and low sag. It is easily soluble in oilfield acids. MicroDense is milled to a D50 of 5μ and a D90 15μ .

Features and Benefits

MicroDense is approximately 10% denser and over 60% harder than barite but with significantly lower abrasiveness than barite or hematite. These properties provide benefits enabling the use of MicroDense to provide density with better Sag control and ECO management.

International Shipping References

Transportation of MICRODENSE is not restricted by any regulatory agency. MicroDense is not classified as Hazardous.

Safe Handling Recommendations

Utilize normal precautions for employee protection when handling chemical products. Utilize appropriate respirator, gloves, goggles and apron. Refer to the Material Safety Data Sheet (MSDS) for this product prior to use.

Typical Physical Properties

- Physical State: Solid
- Max Temperature: 400
- Reservoir Compatible: Both
- Category: Weighting Agents
- Sub Category: Micronized Ilmenite
- Product Tier: X-Premium
- SG value: 4.5
- Appearance: Black powder
- Specific Gravity: 4.5 - 4.6
- Bulk Density Kg/m^3 : 2400 - 2700
- Particle size (μm): 5

Product Function

MICRODENSE will settle around 8 times slower than Barite. ECD Management: The small particle size, shape and inertness of MicroDense produces fluids with significantly lower rheologies. Formation Damage Mitigation: MicroDense can be easier flow back through the formation. It is also soluble in oilfield acids such as HCl, Organic acids and Chelating agents. It is compatible with all fluid systems and additives including other weighting materials. Can supplement to lower the use of other weighting materials such as Barite with significantly improved rheology, Sag & ECD. MICRODENSE is a great option to densify fluids on restricted ECD applications.

Recommended Treatment

Treatment levels are determined by specified requirements.

Standard Packing

MicroDense is packaged in 25 kgs multiwall paper sack, 1 or 1.5 MT big bags. MICRODENSE is a Registered Trade Mark product of ELKEM.

+971 2 610 7000

info@ppc.ae | www.ppc.ae

Abu Dhabi | UAE



DRILLING FLUIDS SOLUTIONS
A MAZRAI ENERGY SERVICES COMPANY

Petrochem Performance Chemicals Limited LLC believes in good faith that the information presented in this bulletin is accurate and reliable. No other representation or warranties are given or made in relation to the information or the products of whatsoever nature, and Petrochem Performance Chemicals Limited LLC assumes no responsibility for advice or recommendations made herein or any other information disseminated concerning this product. Petrochem Performance Chemicals Limited LLC will replace or issue credit for the purchase price of any product determined to be defective at delivery. Under no circumstances shall Petrochem Performance Chemicals Limited LLC or its responsible personnel be liable for any special or consequential damages whatsoever.